

Re-Tek Products  
 3320 Cleaton Road  
 Central City, KY 42330  
 Phone (502) 241-0980  
 Fax (502) 241-0987

PRODUCT DATA SHEET

Product: 4-6 mm Black SBR

Product Description: Granulated cured black SBR compound, 4-6 mm in size, having a nominal specific gravity of 1.14, free of fabric and foreign material.

| Chemical Properties  | PRODUCT ANALYSIS |      | TEST METHOD |
|----------------------|------------------|------|-------------|
|                      | Min.             | Max. | D-297       |
| Acetone Extract      | 14.0             | 22.0 |             |
| Ash Content          |                  | 8.0  |             |
| Carbon Black Content | 27.0             | 33.0 | Difference  |
| Rubber Hydrocarbon   | 42.0             |      |             |

---

| Physical Properties | U.S Standard Screen                      | % Retained  | D-1511 |
|---------------------|--|-------------|--------|
| Sieve Analysis      |  |             |        |
|                     | 3 Mesh                                   | 0-10%       |        |
|                     | 5 Mesh                                   | 60-85%      |        |
|                     | Pan                                      | 0-5%        |        |
|                     | Specific Gravity                         | 1.12 - 1.17 | D-297  |
|                     | Moisture :                               | 1% Maximum  | D-1509 |
|                     | Bulk Density: Approximately 20# / Cu. ft |             |        |
|                     | Free Flowing Agent Additive: 2%/WT. Max. |             |        |

A Guideline Specification Only. Provided for the review and approval of a design professional to determine the proper use and suitability of this material for the installed use and purpose intended.